KHUA®
ZHEJIANG GUANGHUA TECHNOLOGY

Technical Data Sheet

GH-2240

Version: Feb 01,2022

.

POWDER COATING RESINS	TGIC
PE : HARDENER = 93 : 7	

Description

GH-2240 is a saturated carboxylated polyester resin designed for 93/7 TGIC powders to be cured at 200°C. Coatings based on GH-2240 combine a excellent flow, and good outdoor durability.

Item	Limits
Appearance	Pale granules
Acid value (mg KOH/g)	32 - 38
Viscosity @ 200 °C, (mPa.s)	2400 - 3600
Color(b*)	Max 10

Specification

Item	Typical value
Glass transition temperature (°C)	60

Other

Storage conditions

The resin in its original unopened bags is stable for more than 1 year, stored in a dry place at temperature below 30°C. Avoid direct sunlight.

Delivery form

Granules. White opaque polyethylene bags of 25kg. One ton per pallet.

Component	Weight (g)
GH-2240	558
TGIC	42
TiO_2	386
Flow agent	10
Benzoin	4

Starting Formulation

Application/Extrusion Conditions

Extrusion	
Extruder	Twin screw
Speed	250 rpm
1st Zone Temperature	100 °C
2nd Zone Temperature	115 °C
Application	
Application	70 micrometer film on 0.5 mm chromated Al panel

Test Items	Result
Film thickness (microns)	60-80
Gloss @ 60° (%)	94
Cupping test (mm)	9
Direct impact (kg.cm)	80
Reverse impact (kg.cm)	80
Adhesion (grade)	0
Spray Gun	Output voltage: 70 kV
Curing	15 min @ 200° C metal temperature

Coating Properties

System Properties

- ❖ Good weathering resistance

ZHEJIANG GUANGHUA TECHNOLOGY CO., LTD www.khua.com	Customer Service	Technical Service
	Tel. 86-573-87771555 Fax 86-573-87771222	Tel. 86-573-87771188 Fax 86-573-87771222

Although the facts and suggestions in this publication are based on our own research and are believed reliable, we cannot assume any responsibility for performance or results obtained through the use of our products herein described, nor do we accept any liability for loss or damages directly or indirectly caused by our products. The user is held to check the quality, safety and all other properties of our product prior to use. Nothing herein is to be taken as permission, inducement or recommendation to practise any patented invention without a license.

- ❖ Excellent flow

	Region	Customer Service		Technical Service	
Surface Specialties S.A./N.V. **Anderlecht Str., 33** **B-1620 Drogenbos** **Belgium**	North America U.S.A	Tel. Fax	800-433-2873 770-970-8370	Tel. Fax	770-970-8313 770-970-8702
	Europe/Africa Belgium	Tel. Fax	+32(2) 334-5111 +32(2) 378-3944	Tel. Fax	+32 (2) 334 5172 +32 (2) 378 3944
	Europe/Africa Italy	Tel. Fax	+32(2) 334-5111 +32(2) 378-3944	Tel. Fax	+39 0424 516 611 +39 0424 516 725
www.surfacespecialties.com	Asia Pacific	Malaysia Tel. Fax	 +60(3) 7861 3188 +60(3) 7861 3100	Thailand Tel. Fax	 +66(2) 753 0922 +66(2) 384 5892

Disclaimer: Surface Specialties S.A./N.V. or any of its affiliated companies (hereinafter "Surface Specialties") decline any liability with respect to the use made by any third party of the information contained herein. The information contained herein represents Surface Specialties' best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Surface Specialties is the sole owner or authorized user of the intellectual property rights relating to the information communicated. The information relating to the use of the products is given for information purposes only. No guarantee or warranty is provided that the product is adapted to the client's specific use. The client should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product remains the sole responsibility of the client. ™Trademark of Surface Specialties Group