

EP-2150

Version: March 12,2018

**RESINS FOR CLEAN
EXTRUDER**

SPECIAL

Description

EP-2150 is a special resin for cleaning extruder.

Specification

Item	Limits
Appearance	Pale granules
Hydroxyl value (mg KOH/g) Calculated value	28 - 35
Viscosity @ 200 °C, (mPa.s)	20000 - 30000
Color, b value	Max 10

Other

Item	Typical value
Glass transition temperature (°C)	56
Melting Point (°C)	195-205

Storage conditions

The resin in its original unopened bags is stable for more than 1 year, stored in a dry place at temperature below 30°C. Avoid direct sunlight.

Delivery form

Granules. White opaque polyethylene bags of 25kg.
One ton per pallet .

ZHEJIANG GUANGHUA TECHNOLOGY CO., LTD www.zjquanghua.com	Customer Service	Technical Service
	Tel. 86-573-87771555 Fax 86-573-87771222	Tel. 86-573-87771188 Fax 86-573-87771222

Although the facts and suggestions in this publication are based on our own research and are believed reliable, we cannot assume any responsibility for performance or results obtained through the use of our products herein described, nor do we accept any liability for loss or damages directly or indirectly caused by our products. The user is held to check the quality, safety and all other properties of our product prior to use. Nothing herein is to be taken as permission, inducement or recommendation to practise any patented invention without a license.