

Version: Aug 30,2017



**EP-3121** 

POWDER COATING RESINS

PRIMID

**PE: HARDENER = 95:5** 

# **Description**

EP-3121 is a saturated carboxylated polyester resin designed for 95/5 Primid powders to be cured at 180°C. Coatings based on EP-3121 combine a good mechanical properties together with an excellent over-baking resistance.

### **Specification**

Item	Limits
Acid value (mg KOH/g)	32 - 36
Viscosity @ 200 °C, (mPa.s)	3200 - 4500
Color, b value	Max 10

#### Other

Item	Typical value
Glass transition temperature (°C)	62

#### Storage conditions

The resin in its original unopened bags is stable for more than 1 year, stored in a dry place at temperature below 30°C. Avoid direct sunlight.

# **Delivery form**

Granules. White opaque polyethylene bags of 25kg. One ton per pallet .

## **Starting Formulation**

Component	Weight (g)
EP-3121	570
XL-552	30
TiO <sub>2</sub>	386
Flow agent	10
Benzoin	4

#### **Application/Extrusion Conditions**

Extrusion			
Extruder		Twin screw	
Speed		40 HZ	
1st Zone Tempera	ature	100 °C	
2 <sup>nd</sup> Zone Temperature		120 °C	
Application			
Application	70 micrometer film on 0.5 mm chromated Al panel		
Spray Gun	Output voltage: 70 kV		
Curing	10 min @ 180° C metal temperature		

### **Coating Properties**

Test Items	Result
Film thickness (microns)	60-80
Gloss @ 60° (%)	90
Cupping test (mm)	10
Direct impact (kg.cm)	80
Reverse impact (kg.cm )	80
Adhesion (grade)	0

# **System Properties**

- Very good durable ability
- Outstanding mechanical properties
- ❖ Good over-baking resistance

	Customer Service	Technical Service	
ZHEJIANG GUANGHUA TECHNOLOGY CO., LTD	Tel. 86-573-87771555	Tel. 86-573-87771188	
www.khua.com	Fax 86-573-87771222	Fax 86-573-87771222	

Although the facts and suggestions in this publication are based on our own research and are believed reliable, we cannot assume any responsibility for performance or results obtained through the use of our products herein described, nor do we accept any liability for loss or damages directly or indirectly caused by our products. The user is held to check the quality, safety and all other properties of our product prior to use. Nothing herein is to be taken as permission, inducement or recommendation to practise any patented invention without a license.