

EP-4106

Version: Aug 30,2017

POWDER COATING RESINS	PRIMID
PE : HARDENER = 97 : 3	

Description

EP-4106 is a saturated carboxylated polyester resin designed for 97/3 Primid powders to be cured at 180°C. Dry blending with EP-4107 at ratio 1/1 to produce powder coating with 60° gloss between 30-35%. The coating shows very good mechanical properties and weathering resistance that meet Qualicoat specifications.

Specification

Item	Limits
Acid value (mg KOH/g)	19 - 22
Viscosity @ 200 °C, (mPa.s)	6000 - 10000
Color,b value	Max 15

Other

Item	Typical value
Glass transition temperature (°C)	61

Storage conditions

The resin in its original unopened bags is stable for more than 1 year, stored in a dry place at temperature below 30°C. Avoid direct sunlight.

Delivery form

Granules. White opaque polyethylene bags of 25kg. One ton per pallet .

Starting Formulation

Component	Weight (g)	Weight (g)
EP-4106	582	---
EP-4107	---	558
XL-552	18	42
TiO ₂	386	386
Flow agent	10	10
Benzoin	4	4

Application/Extrusion Conditions

Extrusion	
Extruder	Twin screw
Speed	250 rpm
1 st Zone Temperature	100 °C
2 nd Zone Temperature	120 °C
Application	
Application	70 micrometer film on 0.5 mm chromated Al panel
Spray Gun	Output voltage: 70 kV
Curing	10 min @ 180° C metal temperature

Coating Properties

Test Items	Result
Film thickness (microns)	60-80
Gloss @ 60° (%)	30-35
Cupping test (mm)	7
Direct impact (kg.cm)	80
Reverse impact (kg.cm)	80
Adhesion (grade)	0

System Properties

- ❖ Very good weathering resistance
- ❖ Very good mechanical properties
- ❖ Gas-oven resistance
- ❖ Good flow

ZHEJIANG GUANGHUA TECHNOLOGY CO., LTD www.khua.com	Customer Service	Technical Service
	Tel. 86-573-87771555 Fax 86-573-87771222	Tel. 86-573-87771188 Fax 86-573-87771222

Although the facts and suggestions in this publication are based on our own research and are believed reliable, we cannot assume any responsibility for performance or results obtained through the use of our products herein described, nor do we accept any liability for loss or damages directly or indirectly caused by our products. The user is held to check the quality, safety and all other properties of our product prior to use. Nothing herein is to be taken as permission, inducement or recommendation to practise any patented invention without a license.