

EP-6102

Version: Aug 30,2017

**POWDER COATING
RESINS**

PU

PE : HARDENER = 93 : 7

Description

EP-6102 is a saturated hydroxylated polyester resin designed for 93/7 Powderlink 1174 powders to be cured at 200°C with catalyst 32-18A. Coatings based on EP-6102 combine an excellent mechanical properties and uniform wrinkle finish.

Specification

Item	Limits
Hydroxyl value (mg KOH/g)	30-35
Viscosity @ 200 °C, (mPa.s)	11200 - 14200
Color,b value	Max 10
Acid value (mg KOH/g)	Max 10

Other

Item	Typical value
Glass transition temperature (°C)	67

Storage conditions

The resin in its original unopened bags is stable for more than 1 year, stored in a dry place at temperature below 30°C. Avoid direct sunlight.

Delivery form

Granules. White opaque polyethylene bags of 25kg. One ton per pallet .

Starting Formulation

Component	Weight (g)
GH-6602	646
1174	48
32-18A	6
TiO ₂	280
Flow agent	10
Benzoin	10

Application/Extrusion Conditions

Extrusion	
Extruder	Twin screw
Speed	250 rpm
1 st Zone Temperature	100 °C
2 nd Zone Temperature	130 °C
Application	
Application	70 micrometer film on 0.5 mm chromated Al panel
Spray Gun	Output voltage: 70 kV
Curing	10 min @ 200° C metal temperature

Coating Properties

Test Items	Result
Cupping test (mm)	7
Direct impact (kg.cm)	80
Reverse impact (kg.cm)	80
Adhesion (grade)	0

System Properties

- ❖ Excellent mechanical properties
- ❖ Uniform wrinkle finish

ZHEJIANG GUANGHUA TECHNOLOGY CO., LTD www.khua.com	Customer Service	Technical Service
	Tel. 86-573-87771555 Fax 86-573-87771222	Tel. 86-573-87771188 Fax 86-573-87771222

Although the facts and suggestions in this publication are based on our own research and are believed reliable, we cannot assume any responsibility for performance or results obtained through the use of our products herein described, nor do we accept any liability for loss or damages directly or indirectly caused by our products. The user is held to check the quality, safety and all other properties of our product prior to use. Nothing herein is to be taken as permission, inducement or recommendation to practise any patented invention without a license.